

DENSITY (Kg/mc)	CEMENT 3.25 (kg)	WATER (lt)	FOAM (lt)	RESISTENCE (Kg/cmq)	THERMAL CONDUCTIBILITY (λ)
300	240	144	850 max	5	0,060
400	300	190	770 max	8	0,082
500	400	240	700 max	15	0,090
600	480	288	640 max	25	0,11